

RESIWOOD[®] SYSTEM TG6 TIMBER GROUT

PRODUCT CODE: 3480 - 2.5 litre pack: 3482 – 7.5 litre (multi pack)
DESCRIPTION: TG6 TIMBER GROUT is one of a series of specially developed epoxy resin systems for the structural repair of timber.

PACKAGING: TG6 TIMBER GROUT is supplied in 5 litre or 20 litre plastic pails. Each pail contains the correct amount of filler, resin and curing agent for the appropriate pack size. (See mixing instructions)

PREPARATION: Timber surfaces should be clean, free from dust and loose or friable particles.
 TG6 TIMBER GROUT is free flowing and very searching. Any cracks or apertures must be adequately sealed with Rotafix P7 BONDING PASTE before mixing and pouring. Where timber preservatives are involved, please consult our Technical Department.



MIXING: The contents of the base resin container/s and the curing agent container/s should be thoroughly mixed in the outer container. The total amount of the filler is then added to the liquid and mixed for 2-3 minutes. Mechanical mixing using the appropriate Rotafix paddle is strongly advised for the 2.5 litre pack and essential for the 7.5 litre pack. The 7.5 litre pack is made up of 3 x 2.5 litre units. If the full 7.5 litres is to be used then all packs need to be mixed in one container. The 2.5 litre units can also be mixed individually if a smaller amount of material is required.

APPLICATION: The volume of material required for a particular pour should be pre-calculated. The mixed TG6 TIMBER GROUT should then be poured or pumped in such a way that there is a continuous head.



COVERAGE: When mixed both pack sizes of TG6 TIMBER GROUT will give the stated volumes of finished grout. As a guide, an 7.5 litre pack would fill a void of 100mm x 100mm x 750mm

CURE SCHEDULE: Rate of cure and exotherm will be related to ambient temperature, material temperature, volume of material poured and the aspect ratio of the pour. For specific information on individual placements in excess of 50 litres please consult our Technical Department.

Workability:	Cure Schedule	Peak Exotherm	
		Not insulated	Insulated
90 mins at +10°C	3 Days at + 10°C	At 10°C to 20°C	30°C
50 mins at + 20°C	2 Days at + 20°C	At 20°C to 25°C	40°C
30 mins at + 30°C	2 Day at + 30°C	At 30°C to 45°C	60°C

CURED PROPERTIES:



Compressive strength >50N/mm². Tensile strength 17N/mm²) Provisional
 Specific Gravity 1.6 Flexural strength 32N/mm²)
 Static Modulus of Elasticity E_C8.3 9KN/mm²)
 Standard colour - Dark Green Colour stable
 Minimum application temperature +5°C.

SPECIFIC USES: Replacement of decayed timber, timber beam upgrading.

CLEANING TOOLS: Uncured TG6 TIMBER GROUT may be readily removed with Rotafix S200 PC Solvent Cleaner. Mechanical methods are required to remove cured material.

The requirements for a Rotafix product(s) may be specific for an individual project.
 Advice given by Rotafix can only be considered as part of the contract if it is provided in writing.
 Epoxy resins and their associated curing agents can cause irritation to some people.
 Please take the necessary precautions indicated in the COSHH details available from our offices.
 Please read our Users Safety Guide on the Handling of Resin and Polymer products.

The information in this document is based on practical tests, but given without guarantee inasmuch as methods of use by others is beyond our control. Due to continuing development and improvements, it may be necessary to change without notice the material specification. All goods are sold subject to our Standard Conditions of Sale.

RESIWOOD is a Registered Trade Mark of Rotafix (Northern) Ltd



ROTAFIX, ROTAFIX HOUSE, ABERCRAF,
 SWANSEA SA9 1UR. U.K.

TEL: +44 (0)1639 730481 FAX: +44 (0)1639 730858
 e.mail: sales@rotafix.co.uk web site: www.rotafix.co.uk

SOUTHERN AREA CONTACT:

TEL: +44 (0)1442 243169 FAX: +44 (0)1442 234901