

VINACRETE W.B. TEXTURED OR SMOOTH

PRODUCT 3522 - 5 litre Smooth 3523 - 15 litre Smooth
CODE: 3524 - 5 litre Textured 3525 - 15 litre Textured

DESCRIPTION: VINACRETE WB is a high performance acrylic based masonry coating containing specially graded fillers. Standard colour white.

PACKAGING: Supplied in 5 litre plastic pails, approximately 7.5 kilograms and 15 litre pails - 22.5 kilograms.

PREPARATION: Surfaces should be dry and free from grease, oil and other contaminants. Any loose and friable concrete should be brushed down. Rotafix Vinachem code 3520 should be used as a primer/adhesion promoter, particularly on porous or dusty surfaces.

MIXING: Stir well before use.

APPLICATION: Apply by brush. One application over a suitably primed surface is normally sufficient on an even substrate. If further coats are required leave 24 hours between applications.

COVERAGE and CURED PROPERTIES: Coverage varies considerably depending upon the nature of the substrate and amount of Vinacrete applied. A medium texture on a substrate of average porosity uses approximately 1 litre of vinacrete per 3m²
VINACRETE SMOOTH depending on the nature of substrate 1 litre will cover approximately 4m².

CURE SCHEDULE: 2 - 4 hours dependent upon conditions. Over-coat 12 - 20 hours.

SPECIFIC USES: VINACRETE WB is used for the protection of new and repaired concrete structures. It has excellent weathering properties and contributes towards the prevention of carbonation.

CLEANING OF TOOLS: Uncured VINACRETE WB may be readily removed from tools and equipment with warm water containing soap or detergent. Mechanical methods are required to remove cured material.

Use in well ventilated area. If spraying use appropriate protection and employ mechanical extraction. Avoid eye and skin contact. In case of contact with eyes rinse immediately with plenty of water. Seek medical advice
If in doubt about conditions of use, contact our Technical Department prior to use.

The information in this document is based on practical tests, but given without guarantee insomuch as methods of use by others is beyond our control. Due to continuing development and improvements, it may be necessary to change without notice the material specification. All goods are sold subject to our Standard Conditions of Sale.

ROTAFIX, ROTAFIX HOUSE, ABERCRAF, SWANSEA SA9 1UR. U.K.
TEL: +44 (0)1639 730481 FAX: +44 (0)1639 730858
e.mail: sales@rotafix.co.uk Website: www.rotafix.co.uk

SOUTHERN AREA CONTACT: TEL: +44 (0)1442 243169 FAX: +44 (0)1442 234901

