



## P12CR PRIMER (BS6920)

- PRODUCT CODE:** 3336
- DESCRIPTION:** Rotafix **P12CR PRIMER (BS 6920)** is a 2-part epoxy resin system which conforms to **BS 6920**.
- PACKAGING:** Available in 1 litre packs.
- PREPARATION:** Ensure all substrate is clean and free from grease.
- MIXING:** The contents of the hardener (curing agent) are added to the contents of the base resin container and mixed thoroughly.
- APPLICATION:** Apply to clean concrete stone or steel with brush or roller.
- COVERAGE:** 1 litre covers approximately 3m<sup>2</sup> on stone, or 5m<sup>2</sup> on steel.
- CURE SCHEDULE:** 20 minutes pot life at 20°C ambient. 2 hours touch dry when coated over substrate.
- CURED PROPERTIES:**
- |                       |                      |
|-----------------------|----------------------|
| Compressive Strength: | >50N/mm <sup>2</sup> |
| Specific Gravity      | 1.1                  |
| Tensile Strength:     | 17N/mm <sup>2</sup>  |
| Flexural Strength     | 32N/mm <sup>2</sup>  |
- Mix 45 parts Hardener with 100 parts Base
- SPECIFIC USES:** The cured system is suitable for potable water applications.
- APPROVAL:** **P12 PRIMER conforms to the Water Research Council test requirements of BS 6920 for use in potable water situations**
- CLEANING OF TOOLS:** Uncured **P12 (BS 6920)** may be readily removed from tools and equipment with Rotafix **s200 PC** Solvent Cleaner. Mechanical methods are required to remove cured material

Epoxy resins and their associated curing agents can cause irritation to some people. Please take the necessary precautions indicated in the COSHH details available from our offices.  
Please read our Users Safety Guide on the Handling of Resin and Polymer products.

The information in this document is based on practical tests, but given without guarantee inasmuch as methods of use by others is beyond our control. Due to continuing development and improvements, it may be necessary to change without notice the material specification. All goods are sold subject to our Standard Conditions of Sale.

**ROTAFIX, ROTAFIX HOUSE, ABERCRAF, SWANSEA SA9 1UR. U.K.**  
**TEL: +44 (0)1639 730481 FAX: +44 (0)1639 730858**  
**e.mail: sales@rotafix.co.uk Website: www.rotafix.co.uk**

**SOUTHERN AREA CONTACT:**  
**TEL: +44 (0)1442 243169 FAX: +44 (0)1442 234901**